

This Page Is Inserted by IFW Operations  
and is not a part of the Official Record

## **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning documents *will not* correct images,  
please do not report the images to the  
Image Problem Mailbox.**

What is claimed is:

1. A lens sheet comprising a lens portion with a plurality of lens elements arranged in at least one side and a shielding layer provided in a non-transmitting portion of a light radiation plane, wherein the shielding layer is provided on a layer made of a cured photo-curing composition (A), wherein the photo-curing composition (A) is composed of 100 weight parts of photo-curing resin composition (a) having a surface free energy of 30mN/m or more and 0.01 to 10 weight parts of compound (b) having a surface free energy of 25mN/m or less.

2. A lens sheet comprising a lens portion with a plurality of lens elements arranged in at least one side and a shielding layer provided in a non-transmitting portion of a light radiation plane, wherein the shielding layer is provided on a layer made of a cured photo-curing composition (A), wherein a light-transmitting portion in the layer of the photo-curing composition (A) has a surface free energy of 25mN/m or less.

3. The lens sheet according to claim 1 or 2, wherein the lens portion is a group of convex cylindrical lenses one-dimensionally arrayed on a light incidence plane.

4. The lens sheet according to claim 1 or 2, wherein the lens portion is a group of convex lenses two-dimensionally arrayed on a light incidence plane.

5. The lens sheet according to claim 1 or 2, wherein the lens portion is a fresnel lens constituted of fresnel lens faces and rising faces, wherein the fresnel lens faces are obtained by dividing the light radiation plane into the shape of a number of concentric circles and the rising faces each define boundaries of the fresnel lens faces.

6. A method of producing a lens sheet which includes a lens portion with a plurality of lens elements arranged in at least one side and a shielding layer provided in a non-transmitting portion of a light radiation plane, the method comprising the following steps of:

coating photo-curing composition (A) on a light radiation plane of the lens sheet to form a layer made of the photo-curing composition (A), the photo-curing composition (A) being composed of 100 weight parts of photo-curing resin composition (a) having a surface free energy of 30mN/m or more and 0.01 to 10 weight parts of compound (b) having a surface free energy of 25mN/m or less;

radiating light from the side opposite to the layer of the photo-curing composition (A) to selectively cure a light transmitting portion of the layer of the photo-curing composition (A) with the layer of the photo-curing composition (A) being contacted with a medium having free energy lower than that of the compound (b); and

painting colored pigment on the layer of the photo-curing composition (A) to form a shielding layer in a non-transmitting portion of light.

7. The method of producing a lens sheet according to claim 6, wherein said step of forming a shielding layer comprising the steps of:

painting the colored pigment; and

drying the colored pigment after a time period lapses as much as the colored pigment painted on the light transmitting portion is repelled to completely expose the layer of the photo-curing composition (A) in the light transmitting portion.

8. The method of producing a lens sheet according to claim 6, wherein said step of forming a shielding layer comprising the steps of:

painting the colored pigment;

drying the colored pigment; and

removing the colored pigment on the light transmitting portion.

9. The method of producing a lens sheet according to claim 6, wherein the wherein said step of forming a shielding layer comprising the steps of:

painting photo-curing colored pigment on a peelable sheet;

attaching a layer of the photo-curing colored pigment and the layer of the photo-curing composition (A) to each other; and

radiating light from the side opposite to the layer of the photo-curing colored pigment and the photo-curing composites (A) to selectively cure a light transmitting portion of the photo-curing colored pigment; and peeling the peelable sheet from the lens sheet.

10. The method of producing a lens sheet according to claim 6, further

comprising the step of: radiating light from the side opposite to the layer of the photo-curing composition (A) to cure an uncured portion of the layer of the photo-curing composition (A) with the layer of the photo-curing composition (A) being contacted with a medium having free energy higher than that of the photo-curing resin composition (a) between said step of radiating light from the side opposite to the layer of the photo-curing composition (A) to selectively cure a light-transmitting portion of that layer and said step of forming a shielding layer.

11. The method of producing a lens sheet according to one of the preceding claims 6 to 10, wherein the medium having a surface free energy lower than that of the compound (b) is the air.

12. The method of producing a lens sheet according to claim 10, wherein the medium having a surface free energy higher than that of the photo-curing resin composition (a) is water.

13. The method of producing a lens sheet according to one of the preceding claims 6 to 12, wherein the light radiated from the side opposite to the layer of the photo-curing composition (A) propagates substantially in a parallel direction.

14. The method of producing a lens sheet according to one of the preceding claims 6 to 12, wherein the lens sheet is used for a projection screen for an image display device which displays an image by projecting light from rearward, and the light radiated from

the side opposite to the layer of the photo-curing composition (A) propagates substantially in the same direction as that of the projection light of the image.